
**Textiles — Determination of spirality
after laundering —**

**Part 3:
Woven and knitted garments**

*Textiles — Détermination du vrillage après lavage —
Partie 3: Vêtements tissés ou tricotés*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1211 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Web: www.iso.org

Published in Switzerland

Contents		Page
	Foreword	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	2
6	Conditioning	2
7	Test specimen	2
8	Marking procedures	2
	8.1 Procedure A — Garment, within-panel.....	2
	8.1.1 Normal procedure.....	2
	8.1.2 Alternative procedure.....	2
	8.2 Procedure B — Garment, panel sides.....	2
9	Laundering	3
10	Assessment	3
	10.1 General.....	3
	10.2 Assessment by procedure.....	3
	10.2.1 Procedure A — Garment, within-panel.....	3
	10.2.2 Procedure B — Garment, side panel.....	3
11	Test report	3
	Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 2, *Cleansing, finishing and water resistance tests*.

This second edition cancels and replaces the first edition (ISO 16322-3:2005), which has been technically revised. The main changes compared to the previous editions are as follows:

- [Figure 4](#) has been corrected.

A list of all parts in the ISO 16322 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Textiles — Determination of spirality after laundering —

Part 3: Woven and knitted garments

1 Scope

This document specifies procedures to measure the spirality or torque of woven and knitted garments after domestic laundering.

The results obtained from different procedures might not be comparable.

This document is not intended to measure the spirality of garments as manufactured, but rather the spirality after domestic laundering.

NOTE Some fabric constructions, such as denim, can have spirality intentionally introduced during manufacturing. Garments made of fabrics from circular knitting machines can have inherent nonverticality of wale alignment.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 6330, *Textiles — Domestic washing and drying procedures for textile testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 spirality torque

<in garments>rotation, usually lateral, between different panels of a garment resulting from the release of latent stresses during laundering of the woven or knitted fabric forming the garment

Note 1 to entry: The phenomenon is sometimes referred to as twist, for example, denim jean leg twist.

4 Principle

Test specimens are prepared, marked and laundered according to specified procedures. Spirality is measured in percentage of a marked distance.

9 Laundering

- 9.1 Select laundering conditions according to ISO 6330 that correspond to those which the garment will be exposed.
- 9.2 Perform the selected number of laundering cycles.
- 9.3 After the final laundering cycle, condition garments in the standard atmosphere for testing textiles according to ISO 139.

10 Assessment

10.1 General

Specimens should be placed flat on a smooth surface in their natural orientation.

10.2 Assessment by procedure

10.2.1 Procedure A — Garment, within-panel

Place the horizontal leg of a right angle device along line YZ and the second leg on a perpendicular downward from point B. Mark the point where the angle device intersects with line YZ. This is point A' (see [Figure 2](#)).

Measure and record AA'.

Calculate the percentage spirality (X) of each garment to nearest 0,1 % as shown in [Formula \(1\)](#):

$$X = 100(AA'/AB) \quad (1)$$

Calculate and report the mean percentage spirality in the garments tested.

10.2.2 Procedure B — Garment, side panel

The side seam or edge fold at the bottom hemmed edge is marked. This is point A'.

Measure and record line AB and AA' (see [Figure 1](#)).

Calculate the percentage spirality (X) of each garment to the nearest 0,1 % as shown in [Formula \(2\)](#):

$$X = 100 \left(\frac{AA'}{AB} \right) \quad (2)$$

Calculate and report the mean percentage spirality in the garments tested.

11 Test report

The test report shall contain the following:

- a reference to this document, i.e. ISO 16322-3:2021;
- details of garment tested;
- mean percentage spirality of garments prior to laundering, if any;
- mean percentage spirality of the garments tested after laundering;

- e) marking procedure used (A or B);
- f) laundering procedure and type washer used;
- g) number of laundering cycles used;
- h) date of the test;
- i) details of any deviations from the specified procedure.






Figure 1 — Within-garment panel — Marks before laundering

**Key**

- 1 original side seam
- 2 after laundering side edge fold

NOTE The spirality direction in the figure is for illustration only. Spirality can be in either direction.


Figure 2 — Within garment panel — Marks after laundering



Key

- 1 side seam (edge fold)

Figure 3 — Side seam (edge fold) — Garment marks before laundering

**Key**

- 1 original side seam
- 2 after laundering side edge fold

NOTE The spirality direction in the figure is for illustration only. Spirality can be in either direction.

Figure 4 — Side seam (edge fold) — Garment marks after laundering

Bibliography

- [1] ISO 16322-2:2021, *Textiles — Determination of spirality after laundering — Part 2: Woven and knitted fabrics*
- [2] AATCC TM179 *Test Method for Skew Change in Fabrics After Home Laundering*
- [3] AATCC TM207 *Test Method for Seam Twist in Garments Before and After Home Laundering*

Qingdao SINO Textile

